

# **ECORRECT PRIVATE LIMITED**

### ECWS01

#### **BIO COMPOSTABLE GRANULES BLOWN FILM GRADE**

ECWS01 is a Water-Soluble Biodegradable grade suitable for general purpose blown film grade. Films blown from this grade exhibit great elongation. The granules offer a good tensile strength and melt strength.

#### **TECHNICAL VALUES:**

PROPERTY	TEST STANDARD	UNIT	RESULT
Density (23°C)	ASTM D 1505	g/cc	1.332
MFI	ASTM D1238	gms/10 min (190°C at 5Kg Load)	1.23

#### FOR THE FILM PROPERTIES-

Ultimate tensile strength	ASTM 882	MPa	10.0
Tensile strength at yield	ASTM 882	MPa	10.3
Elongation at break	ASTM 882	%	100
Elongation at yield	ASTM 882	%	100

### RECOMMENDED MELTING PROFILE OF THIS GRADE IN 45 MM DIAMETER SCREW BLOWNFILM **MACHINE**

ZONE	TEMPERATURE
1	125
2	127
3	130
4	135 (Candle filter Zone)
5	128 (Die Zone 1)
6	125 (Die Zone 2)











## **ECORRECT PRIVATE LIMITED**

#### **APPLICATIONS:**

Used for producing general purpose blown film and recommended for use in different types of carry bags. ECWS01 granules are compatible to normal plastic (Linear Density-LD) blown film machine.

#### **STORAGE AND SHELF LIFE:**

ECWS01 granules have a minimum shelf life of the one year if kept in dry conditions. Packaging should be resealed after opening to protect against moisture.

The information and data presented herein is true and accurate to the best of our knowledge. No warranty or guarantee expressed or implied, is made regarding performance or otherwise.











**B-137 Garden Villa Society,** 

CIN Number- U25209GJ2020PTC113442